



深圳市賽雅電子漿料有限公司  
Shenzhen Sryeo Electronic Paste Co., Ltd.

Tel : 0755-28078692

Fax : 0755-28078687

[www.sryeo.com](http://www.sryeo.com)(中文)

[www.sryeo.net](http://www.sryeo.net) (Eng.)

[sales@sryeo.com](mailto:sales@sryeo.com)

## 产品规格书/Specification

产品/product:	导电银浆/ Silver paste
料号/Part number:	01H-3303

### 适用范围/Application:

此产品适用于 NTC 热敏电阻产品电极使用

Suitable for NTC ceramic resistor electrode.

### 使用条件/Operating conditions:

基材 Substrate	NTC 热敏电阻陶瓷 NTC ceramic
印刷 Printing	200-300 目丝网印刷 200-300 mesh stainless screen
流平 Levelling	5-15min minutes at room temperature 室温下流平 5-15 分钟 (时间根据流平的实际情况决定)。
干燥 Drying	通风烘箱烘烤 100-150°C, 10-15 分钟 (空考温度低于 300°C, 可根据烘烤的实际情况决定烘烤时间。) 100-150°C 10-15 min
烧结 Firing Condition	隧道炉空气气氛下烧结, 峰值 850±10°C (推荐值), 9-11 分钟。 (可根据实际需要, 烧结范围可在 800-850°C 内调节, 但峰值温度时间必须 10 分钟。) Atmospheric firing in belt furnace with peak time of 9-11 Minutes at 850±10°C
Thinner	ST-1000

### 性能/Characteristics:

#### 1. 浆料性能/Paste Characteristics:

性能 Characteristic	标准 Standard	测试方法及条件 Test method and conditions
1 Fineness	≤5μm	FOG test
2 Viscosity	120-280Pa.s	Brookfield HBT utility cup and spindle (SC4-14/6R), 10rpm, 25±1°C,  Brookfield HBT (博利飞) 粘度计, 转子 SC4-14/6R), 10rpm, 25±1°C 粘度可根据用户实际需要调节。

#### 2. 烧结后特性/Characteristics after firing:

在 1 烧结条件下, 膜厚 8-12μm Check fired film produced under the conditions specified in 1), (Film thickness is 8-12μm.)



深圳市賽雅電子漿料有限公司  
**Shenzhen Sryeo Electronic Paste Co., Ltd.**

Tel : 0755-28078692

Fax : 0755-28078687

[www.sryeo.com](http://www.sryeo.com)(中文)

[www.sryeo.net](http://www.sryeo.net) (Eng.)

[sales@sryeo.com](mailto:sales@sryeo.com)

特性 Characteristics	Standard 标准	测试方法和条件 Test method and conditions
3 Resistivity 方阻	≤5mΩ/□	Test pattern 0.6mm×60mm 测试图形 0.6mm×60mm
4 Adhesion strength 附着力		Peel Test: 0.5mmφ Tin plated Cu wire soldered on 2mm×2mm Pad. 0.5mmφ 锡浸铜线, 焊接面积 2mm×2mm Solder: 96.5Sn/0.5Cu Mildly activated flux used. 焊料: 96.5Sn/0.5Cu
Initial 初始附着力	≥45.2N	
Ageing 老化附着力	≥24.6N	Ageing: 150°C×24hrs 老化条件: 150°C, 24 小时

**保存条件, 有效期/Storage condition and Term of validity**

产品应在 5-25°C 的环境温度下密封储存, 有效期为产品发货之日起 1 年。

The product shall be guaranteed for 1 year after shipping date, keep tightly under at 5-25°C

**包装方式/Packaging method:**

标准包装, 1000g/罐, 样品可提供 200 克小罐包装

Standard package 1000g/can, if you need sample to test, available 200g with small package.